



Description

ZETTEX PU 80 is a one-component, ultra-fast curing, flexible and high performance polyurethane adhesive for the direct glazing of vehicle glass. It is specifically designed to give a fast and safe drive-away time on vehicles fitted with airbags.

Chemical nature

Polyurethane

Advantages

- One-component polyurethane
- Rapid application and curing
- Suitable for cold and warm application
- High Modulus - maintains torsional rigidity and increases the vehicles NVH values
- Capable of withstanding high dynamic stresses
- Non-conductive
- Suitable for use with integral aerials
- Prevents contact corrosion in aluminium-body vehicles

Application

- It is ideal for direct glazing on vehicles where high shear modulus and non-conductive properties are required. Solvent free, it is completely odourless. ZETTEX PU 80 combines a high modulus properties which provides the extra strength required to maintain torsional rigidity, very low volume resistivity and good high-frequency properties, allowing the correct bonding to glass incorporating radio antenna or additional electrical equipment.
- Fit the cartridge into a manual or pneumatic air operated gun (provided with telescopic piston). The surfaces to be treated should be perfectly clean, dry and free from dust and grease. It is necessary to apply a cleaner/activator and a primer on glass. The adhesion on normal vehicle varnishes generally does not require the use of Primer. It is advisable to carry out preliminary adhesion tests on the support. Specific guidance regarding the use of Primers may be obtained by submitting substrate samples to our laboratories.
- Drive Away Time: 30 minutes (throughout operating window of -5°C to $+40^{\circ}\text{C}$)
- On vehicles fitted with both driver and passenger airbags ZETTEX PU 80 meets Federal Motor Vehicle Safety Standards.

Packaging

- Cartridge 310ml

Safety recommendation

- Make sure you have read our MSDS carefully before using this product.

Storage

- ZETTEX PU 80 can be stored for 12 months in its original packing (unopened container) at 10° - 25°C in a cool, dry place. The storage temperature should not exceed 25°C for extended periods of time. Keep away from wet areas, direct sunlight and heat sources.

Zettex Europe B.V.

Blokweg 8 • 4761 RA • Zevenbergen • The Netherlands

T +31 (0)888-93 88 39 • F +31(0)888-93 88 88

I www.zettex.com • E info@zettex.com

Technical data

Chemical nature	Polyurethane
Curing Mechanism	Moisture-curing
Colour	Black
Density [g/cc]	1,28 ± 0,02
Curing through volume [mm] (1 day 23°C and 50% r.h.)	4
Tack-free time [min] (23°C and 50% r.h.)	10-15
Shore A hardness [N/mm ²]	60 – 65
G modulus at 10% [N/mm ²]	≥ 2,5
Tensile strength [N/mm ²] (ISO 37 DIN 53504)	≥ 9
Elongation [%] (ISO 37 DIN 53504)	≥ 350
Electrical volume resistivity [Ω·cm]	1 x 10 ¹⁰
Application temperature [°C]	from +5°C to +40°C
Temperature Resistance [°C]	-40/+100, for short period up to 140

Zettex Europe B.V.

Blokweg 8 • 4761 RA • Zevenbergen • The Netherlands

T +31 (0)888-93 88 39 • F +31(0)888-93 88 88

I www.zettex.com • E info@zettex.com

